

Technical Datas of <i>Passioniss Red</i> Marble	
Mohs Hardness	4 Mohs
Density	2.71 G/cm ³
Weight Per Unit of Volume	2.69 G/cm ³
Absorption of Superheated Water	0,49%
After Frost Compressive Strength	76.32 Mpa
Freezing Loss	0%
Impact resistance	12 Kgf.cm/cm ³
Bending resistance	13.5 Mpa
Apparent porosity	2,04%
Compactness ratio	97,96%
Degree of porosity	2,04%
Average of abrasion resistance	23.2 cm ² /50 cm ²
Compressive Strength	95.5 Mpa
Water absorption coefficient by capillarity	0.425 G/m ² .s0.5
Determination of water absorption at atm.press.	0,71%

Contact:

Minerya, Toros Mah. 818 Sok. No: 10/2 Konyaaltı/Antaly, Turkey
<http://www.minerya.com.tr>

Durhan Cinciođlu, Tel: +90 5075264616, Cel: +90 242 871
4411,

Mail: durhan@minerya.com.tr,

Oktay obanođl, Tel: +905332575488,

Cel: +90242 871 4411,

Mail: oktay@minerya.com.tr, oktay@cobanoglumaden.com